



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number : **0 528 602 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **92307235.9**

(51) Int. Cl.⁵ : **C09B 67/08**

(22) Date of filing : **07.08.92**

(30) Priority : **16.08.91 GB 9117765**

(43) Date of publication of application :
24.02.93 Bulletin 93/08

(84) Designated Contracting States :
CH DE DK ES FR GB IT LI

(71) Applicant : **CIBA-GEIGY AG**
Klybeckstrasse 141
CH-4002 Basel (CH)

(72) Inventor : **Bugnon, Philippe**
La Chenalyete
CH-1724 Essert (CH)
Inventor : **Iqbal, Abul**
La Dey 202
CH-1732 Arconciel (CH)
Inventor : **MacLennan, Alison**
18 Thriplee Road
Bridge of Weir, Renfrewshire (GB)
Inventor : **Fraser, Iain Frank**
45 Stoneyholm Road
Kilbirnie (GB)

(74) Representative : **Sharman, Thomas et al**
CIBA-GEIGY PLC. Patent Department, Central
Research, Hulley Road
Macclesfield, Cheshire SK10 2NX (GB)

(54) **Method of improving storage stability of pigments.**

(57) A method of improving the storage stability of a coloured organic pigment in powder form which comprises coating pigment particles with a solid polymer which is a polar group - containing vinyl polymer, said polar group being a hydroxy, carboxyl, carboxylic ester, anhydride or carboxamide group, or a cellulosic polymer, thereby inhibiting reduction of tinting strength of the pigment on storage.

EP 0 528 602 A1

This invention relates to a method of improving the storage stability of pigments, particularly coloured organic pigments, in powder form, and to storage stable pigment compositions.

It has been found that the tinting strength of a pigment in powder form tends to decrease with increased storage time of the powder. This problem is particularly notable with monoazo pigments.

5 It has now been found that by forming on pigment particles a coating of a solid polar group - containing vinyl or cellulosic polymer, storage stability and therefore retention of tinting strength of pigments in powder form can be significantly improved.

10 It is known to coat pigments with polymers to improve their resistance to solvents and to other materials in which they are incorporated. U.S. Patent 4 889 562 describes the coating of organic pigments with cross-linked ethylcellulose to improve their rheological properties.

Accordingly, the present invention provides a method of improving the storage stability of a coloured organic pigment in powder form which comprises coating pigment particles with a solid polymer which is a solid polar group - containing vinyl polymer, said polar group being a hydroxy, carboxyl, carboxylic ester, anhydride or carboxamide group, or a cellulosic polymer, thereby inhibiting reduction of the tinting strength of the pigment on storage.

15 In another aspect, the present invention provides the use of a solid polar group-containing vinyl polymer, said polar group being as hereinbefore defined, or a cellulosic polymer as a powder stabilising coating on coloured organic pigment particles, thereby inhibiting reduction of the tinting strength of the pigment on storage.

20 Examples of polar group - containing vinyl polymers are homopolymers of carboxylic acids such as acrylic acid, methacrylic acid, esters such as alkyl acrylates, alkyl methacrylates, vinyl acetate and vinyl propionate, anhydrides such as maleic anhydride and amides such as acrylamide, methacrylamide and N-vinyl-2-pyrrolidone; copolymers of two or more of the abovementioned monomers; and copolymers of at least one of the abovementioned monomers with at least one other ethylenically unsaturated material, for example styrene, vinyl chloride, or acrylonitrile.

25 Preferred polar group - containing vinyl polymers include N-vinylpyrrolidone polymers and polyhydroxy or polycarboxy vinyl polymers, that is vinyl polymers having, on average, more than one hydroxy or carboxyl group per molecule. Examples of polyhydroxy vinyl polymers are polyvinyl alcohols, which may be, for example, hydrolysis products of vinyl acetate homopolymers or copolymers and which may contain ester, ether or acetal groups as well as hydroxy groups; polymers of hydroxyl-containing acrylic monomers, for example homopolymers of hydroxyalkyl acrylates and hydroxyalkyl methacrylates such as 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, 3-hydroxypropyl acrylate and the corresponding methacrylates, and copolymers thereof with other ethylenically unsaturated monomers such as alkyl acrylates and alkyl methacrylates; and polymers of allyl alcohol, for example homopolymers thereof and copolymers thereof with other ethylenically unsaturated monomers.

35 Preferred polyhydroxy vinyl polymers are polyvinyl alcohols, which may have number average molecular weights of from 5,000 to 100,000, preferably from 10,000 to 50,000, especially from 10,000 to 20,000. Such polymers are readily available commercially or may be prepared using conventional procedures. A polyvinyl alcohol may be formed in situ by hydrolysis of a vinyl acetate polymer in a dispersion of the pigment.

40 Preferred polycarboxy vinyl polymers are polyacrylic acids, which may be homopolymers of acrylic acid or methacrylic acid or copolymers of acrylic and/or methacrylic acid with at least one other ethylenically unsaturated material, for example an acrylic ester such as ethyl acrylate or 2-ethylhexyl methacrylate, an ethylenically unsaturated hydrocarbon such as styrene, α -methylstyrene or 4-methylstyrene, an ethylenically unsaturated amide such as acrylamide or methacrylamide or an ethylenically unsaturated nitrile such as acrylonitrile or methacrylonitrile.

45 Examples of N-vinylpyrrolidone polymers are homopolymers of N-vinyl-2-pyrrolidone and copolymers thereof with at least one other ethylenically unsaturated material, such as styrene, vinyl chloride, acrylonitrile, vinyl propionate or, preferably, vinyl acetate. Preferred N-vinyl pyrrolidone polymers are homopolymers of N-vinyl-2-pyrrolidone. The N-vinyl pyrrolidone polymer preferably has a number average molecular weight of 5000 to 500,000, more preferably 10,000 to 100,000, especially 20,000 to 50,000.

50 Preferred cellulosic polymers are polyhydroxy cellulosic polymers, i.e. those having, on average, more than one hydroxy group per molecule. These include cellulose itself, partial esters of cellulose such as cellulose monoacetate and cellulose ethers such as methylcellulose, ethylcellulose, 2-hydroxyethylcellulose, 2-hydroxypropylcellulose, sodium carboxymethylcellulose, ethyl 2-hydroxyethylcellulose, 2-hydroxyethyl methylcellulose, 2-hydroxypropyl methylcellulose, 2-hydroxybutyl methylcellulose and 2-hydroxyethyl ethylcellulose. A preferred cellulosic polymer is ethylcellulose.

55 In a convenient method of producing the coated pigment, the vinyl or cellulosic polymer, or a solution or dispersion thereof in a liquid, is mixed with a dispersion, preferably an aqueous dispersion, of the pigment until pigment particles are coated with the polymer, and coated pigment particles are separated from the resulting

mixture, usually by filtration. The separated coated pigment particles, obtained, for example, as a presscake, may be dried by heating to form a powder. Preferably a solution of the polymer in water, a water-miscible organic solvent or a mixture thereof is mixed with an aqueous dispersion of the pigment. The pigment dispersion is conveniently formed by redispersing a pigment presscake in water or a mixture of water with a minor amount of a water-miscible organic solvent. The mixture of pigment dispersion and polymer or polymer solution may be heated, if desired. Optimum conditions, such as temperature and stirring times, for particular pigments and coating polymers can readily be determined by simple experiment.

The formation of the polymer coating on the pigment particles may be as a result of adsorption of the polymer on the surface of the pigment. Where the polymer is in solution in an organic solvent, it may be helpful to add water to facilitate adsorption of the polymer on the pigment. If desired the polymer may be precipitated from a solution thereof onto the pigment particles by addition of a precipitant salt such as sodium chloride or sodium sulphate to the mixture of the pigment dispersion and the polymer solution.

The vinyl or cellulosic polymer is generally used in an amount of 0.1 to 20%, preferably 1 to 15%, by weight, of the pigment.

The coating of the vinyl or cellulosic polymer on the pigment particles may be crosslinked by treatment of the polymer with a crosslinking agent therefor. This treatment is conveniently carried out in the liquid medium in which coating of the pigment particles is effected before separation of the coated particles from the medium, although it could be carried out by treating the coated pigment particles with the crosslinking agent after such separation, for example in another solvent or mixture of solvents.

Suitable crosslinking agents include boron oxyacids and their salts, for example boric acids such as orthoboric acid, metaboric acid and polyboric acids and their salts, usually alkali metal salts, and boronic acids, usually akaneboronic acids such as methaneboronic and ethaneboronic acids or arylboronic acids such as phenylboronic acid, and their salts; phosphoric acids, such as orthophosphoric acid, and their salts, usually alkali metal salts; aliphatic and aromatic aldehydes such as formaldehyde, acetaldehyde, propionaldehyde, n-butyraldehyde, isobutyraldehyde, n-valeraldehyde, n-caproaldehyde, n-heptaldehyde, glyoxal, succinic dialdehyde, glutaric dialdehyde, adipic dialdehyde and benzaldehyde; carboxylic acids and their halides or salts, usually di(acid halides) of dicarboxylic acids such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, tetrahydrophthalic acid, hexahydrophthalic acid and phthalic acid; alkylene dihalides, usually C₁ to C₈ alkylene dihalides such as methylene-, ethylene-, ethylidene-, trimethylene-, tetramethylene-, pentamethylene- and hexamethylene dihalides, usually dibromides or, preferably, dichlorides; aluminium salts such as aluminium nitrate, aluminium sulphate, sodium aluminium sulphate or potassium aluminium sulphate; zinc compounds, including salts and complexes such as zinc chloride, zinc acetate, zinc benzoate, zinc glycinate, zinc alaninate, zinc ammonium bicarbonate or zinc ammonium glycinate; and polyisocyanates, usually diisocyanates such as 1,2-propylene-, 1,4-butyne-, pentamethylene-, hexamethylene-, dodecamethylene-, 1,4-cyclohexylene-, and methyl-2, 4-cyclohexylene diisocyanates, 3-isocyanatomethyl-3, 5,5-trimethylcyclohexyl isocyanate (isophorone diisocyanate), 2,4- and 2,6-tolylene diisocyanates and 4,4'-diphenylmethanediisocyanate.

Other suitable crosslinking agents are alkoxides of elements of Group IVA or Group IVB of the Periodic Table, usually having at least two alkoxy groups per molecule, trialkoxides and tetra-alkoxides being preferred. The alkoxides are usually those of tin, lead, germanium or, preferably, of silicon, titanium or zirconium. The alkoxide groups preferably each have from 1 to 4 carbon atoms, as in sec-butoxide or tert-butoxide groups or, especially, methoxide, ethoxide, n-propoxide, isopropoxide or n-butoxide groups.

Further suitable crosslinking agents are inorganic silicon (IV), tin (IV), titanium (IV) and zirconium (IV) compounds, including silicates which form active silica on hydrolysis, e.g. as described in US Patents 3370971 and 3639133, such as silicic acid, metasilicates or sodium silicate, tin (IV) chloride, titanium (IV) oxysulphate, zirconium (IV) acetate, zirconium (IV) nitrate, also known as zirconyl nitrate, zirconium (IV) oxychloride (ZrOCl₂) and zirconium (IV) orthosulphate, also known as zirconyl sulphate; and aluminates which form alumina on hydrolysis, including water-soluble aluminates such as sodium, potassium and magnesium aluminates.

It will be apparent that choice of the crosslinking agent for a particular coating polymer will depend on the nature of the reactive groups present in that polymer. For example, many of the abovementioned crosslinking agents can be used to crosslink hydroxyl- or carboxyl-containing polymers, whereas some of these agents are used normally with hydroxyl- containing polymers and others are used normally with carboxyl-containing polymers.

Preferred crosslinking agents, particularly for use with hydroxyl-containing polymers, include boric acids and their salts, preferably sodium and potassium salts, especially orthoboric acid and sodium tetraborate; phosphoric acids and their salts, preferably sodium and potassium salts, especially sodium orthophosphate; silicon (IV) trialkoxides or tetra-alkoxides, preferably trialkoxysilyl-substituted C₁ to C₈ alkyl esters of acrylic or methacrylic acid, especially 3-(trimethoxysilyl)propyl methacrylate; silicates which form active silica on hydrolysis.

hydrolysis, especially sodium silicate; aluminates which form alumina on hydrolysis; and zirconium (IV) compounds, especially zirconium (IV) acetate. Other preferred crosslinking agents, particularly for use with carboxyl-containing polymers, are zinc compounds, especially zinc acetate.

In a convenient method of effecting treatment of the coated pigment, the crosslinking agent or a solution thereof in water, a water-miscible organic solvent or mixture thereof is mixed with an aqueous dispersion of the polymer-coated pigment and, after crosslinking, pigment particles having a crosslinked coating are separated from the resulting reaction mixture. The aqueous dispersion of the polymer-coated pigment is conveniently that produced by mixing the polymer, or a solution or dispersion thereof, with an aqueous dispersion of the pigment until pigment particles are coated with the polymer as hereinbefore described.


The crosslinking agent may be used in an amount of 0.01 to 1.5 mol, preferably 0.05 to 0.5 mol, per reactive group, e.g. hydroxy, equivalent of the vinyl or cellulosic polymer; it may be added to the coated pigment dispersion directly or as a solution in water, a water-miscible organic solvent such as an alcohol or a mixture thereof.

The mixture of coated pigment dispersion and crosslinking agent generally has a pH of 5 to 10, preferably 7 to 10. The pH is usually controlled by the addition of a water-soluble base to the aqueous medium. Such bases include alkali metal hydroxides and carbonates, conveniently added as aqueous solutions. When an active silica-forming silicate is used as crosslinking agent, the pH of the aqueous dispersion of coated pigment is usually adjusted to 7-10 by addition of a base and the silicate is added slowly together with a hydrolysing acid, usually sulphuric acid, while the pH is maintained above 7.

The reaction mixture may be heated to effect crosslinking, for example to a temperature up to 95°C, preferably 60-95°C. The crosslinking reaction time may be, for example, from 0.1 to 8 hours; in general, reaction is sufficiently complete within 0.2 to 2 hours. The pigment particles having a crosslinked polymer coating can be separated from the reaction mixture by filtration, washed, stored as presscake if desired and then dried to give a coated pigment powder.

Powder compositions comprising particles of a coloured organic pigment coated with a crosslinked solid polar group-containing vinyl polymer, particularly a polyhydroxy vinyl polymer or a polycarboxy vinyl polymer, are novel. Accordingly, the present invention also provides a particulate composition comprising particles of a coloured organic pigment coated with a crosslinked solid polar group-containing vinyl polymer, particularly a polyhydroxy vinyl polymer or a polycarboxy vinyl polymer. The vinyl polymer and the crosslinking agent are as hereinbefore described, i.e. the polymer is preferably a polyvinyl alcohol which is preferably crosslinked by a boric acid or a salt thereof, a phosphoric acid or a salt thereof, a silicon (IV) trialkoxide or tetra-alkoxide, a silicate which forms active silica on hydrolysis, an aluminate which forms alumina on hydrolysis, or a zirconium (IV) compound, or a polyacrylic acid which is preferably crosslinked by a zinc compound.

In the method and composition of the invention, the pigment may be, for example, a monoazo pigment, a diazo pigment, a phthalocyanine, a quinacridone, an indanthrone, a flavanthrone, a pyranthrone, a perylene, a thioindigo, a dioxazine, a perinone, an isoindoline, an isoindolinone, a diketopyrrolopyrrole, a basic dye complex or a metal complex. The invention is particularly useful where the pigment is a monoazo pigment, for example an arylamide pigment of formula



where Ar¹ denotes a phenyl group substituted by one or two substituents selected from C₁ to C₄ alkyl (preferably methyl), halogen (preferably chlorine), nitro or C₁-C₄ alkoxy (preferably methoxy) and Ar² denotes a phenyl group which is unsubstituted or substituted by one or two substituents selected from C₁-C₄ alkyl (preferably methyl), C₁ to C₄ alkoxy (preferably methoxy) and halogen (preferably chlorine); or a pigment of formula



where Ar¹ is as defined above and Ar³ denotes a 2-hydroxynaphthyl group which may be further substituted by a group -CONHAr² where Ar² is as hereinbefore defined. Such pigments include C.I. Pigments Yellow 1, Yellow 3, Yellow 4, Yellow 5, Yellow 73, Yellow 98, Yellow 111 and, especially, Yellow 74; and C.I. Pigments

Red 3, Red 12 and, especially, Orange 5. The invention is also particularly useful where the pigment is a basic dye complex such as C.I. Pigment Violet 3.

Various co-additives may be used together with a pigment treated according to the invention in pigment compositions. Examples of such co-additives, which are generally used in a total amount of 1 to 50% by weight of the total pigment composition, include surfactants, resins and long chain fatty acids and amines. Surfactants used may be of the anionic type, such as fatty acid taurides, fatty acid N-methyltaurides, fatty acid isothionates, alkylbenzenesulphonates, alkylnaphthalenesulphonates, alkylphenol polyglycol ether sulphates and fatty alcohol polyglycol ether sulphates; fatty acids, such as palmitic, stearic and oleic acids; soaps such as alkali metal salts of fatty acids and naphthenic acids; cationic surfactants include quaternary ammonium salts, and N-oxides of tertiary amines or salts thereof; non-ionic surfactants include fatty alcohol polyglycol ethers (ethoxylated fatty alcohols), fatty acid polyglycol esters, alkylphenol polyglycol ethers and dialkyl polyglycol ethers. Resins include wood rosin, hydrogenated wood rosin, and polyamide resins e.g those produced by condensing phthalic anhydride with long chain amines. Amines which may be added include long chain primary amines e.g. stearylamine; amine derivatives of wood rosin; N-long chain alkylalkylene diamines; polyamines; beta-amines, polyamide/polyamine derivatives of ethoxylated fatty amines and diamines, and derivatives of these compounds.

The present invention also provides a high molecular weight material pigmented with a pigment treated by the method of the invention as hereinbefore described, including high molecular weight material pigmented with the novel particulate compositions as hereinbefore defined. High molecular weight materials which may be pigmented with a pigment treated in accordance with the invention include cellulose ethers and esters such as ethylcellulose, nitrocellulose, cellulose acetate, cellulose butyrate, aminoplasts such as urea-formaldehyde and melamine-formaldehyde resins, alkyd resins, phenoplasts, polycarbonates, polyolefines, polystyrenes, polyvinyl chlorides, polyamides, polyurethanes, polyesters, rubbers, casein and silicones. These high molecular weight materials may be in the form of solids or liquids or in solution, for example in spinning solutions, varnishes, paints and printing inks. The coated pigments produced by the method of the invention are generally incorporated in an amount of 0.01 to 30%, preferably 0.1 to 15%, by weight of the high molecular weight material.

The improved storage stability which can be achieved by the present invention is particularly useful for pigments to be used with high molecular weight materials such as alkyd resins in surface coating compositions such as paints or printing inks.

The invention is illustrated by the following Examples, in which parts and percentages are by weight unless otherwise indicated.

Example 1

C.I. Pigment Yellow 74 aqueous presscake (33% solids) (182g) is re-dispersed in 600 ml water in a conventional manner. To the resulting aqueous suspension at room temperature is added a solution of a polyvinylalcohol having a number average molecular weight of 14,000 (6.1g, 10% on pigment weight) dissolved in water (300 ml). The mixture is stirred for 2.5 hours. A solution of boric acid (1.71 g, 0.2 mol per mol of vinyl alcohol) dissolved in water (60 ml) is added. The temperature is raised to 80°C and the pH increased to 8.1 by addition of dilute aqueous sodium hydroxide. The mixture is stirred for 1 hour at 80°C. After cooling to 70°C, the product is isolated by filtration, washed with water and kept as presscake. The presscake is dried at 65°C in an oven just prior to testing. The product thus obtained is found to have improved powder storage stability compared with the untreated pigment (see Table 1).

Example 2

CI Pigment Yellow 74 aqueous presscake (33% solids) (60g) is re-dispersed in 100g of a 2% solution of ethylcellulose in isopropanol (10% ethylcellulose on pigment weight). Isopropanol (150 ml) is added and the mixture is stirred for 85 minutes. Water (250 ml) is then added over 75 minutes at room temperature. A solution of sodium tetraborate (0.33g, 0.2 mol per mol of ethylcellulose) in water (20 ml) is added. The temperature is raised to 70°C and the pH increased to 7.8 by addition of dilute aqueous sodium hydroxide. The mixture is stirred for 1 hour at 70°C. The product is isolated by filtration, washed with water and kept as presscake. The presscake is dried at 65°C just prior to testing. The product thus obtained is found to have improved powder storage stability compared with the untreated pigment.

Example 3

CI Pigment Yellow 74 aqueous presscake (33% solids) (182g) is re-dispersed in water (700 ml) in a conventional manner. To the resulting aqueous suspension at room temperature is added a solution of a polyvinyl alcohol having a number average molecular weight of 14,000 (6.0g) dissolved in water (600 ml). The mixture is stirred for 17 hours, sodium tetraborate (4.14g) (0.08 mol per mol of vinyl alcohol) is added and the temperature is increased to 85°C. The mixture is stirred at 85°C for 90 mins. After cooling to 70°C, the product is isolated by filtration, washed with water and kept as presscake. The presscake is dried at 65°C, just prior to testing. The product thus obtained is found to have improved powder storage stability compared with the untreated pigment (see Table 1).

Example 4

To a CI Pigment Yellow 74 aqueous slurry (8.4% pigment) (806g) is added a solution of a polyvinyl alcohol having a number average molecular weight of 14,000 (6.8g) in water (100 ml). The slurry is stirred for 15 minutes and heated at 85-90°C for 15 minutes. After cooling to 70°C, the product is isolated by filtration, washed with water and dried at 70°C in an oven. The dried product is sieved and tested and found to have improved powder storage stability compared with the untreated pigment (see Table 2).

Example 5

C.I. Pigment Yellow 74 aqueous presscake (32% solids) (188g) is redispersed in water (700 ml) in a conventional manner. To the resulting aqueous suspension at room temperature is added a solution of a polyvinyl alcohol having a number average molecular weight of 18,000 (6.0g, 10% on pigment weight) in water (500 ml). The mixture is stirred for 3 hours and allowed to stand overnight. The temperature of the mixture is then increased to 75°C and the pH is increased to 8.5 by addition of dilute aqueous sodium hydroxide. After stirring at 75°C for 90 minutes, a solution of 3-(trimethoxysilyl)propyl methacrylate (1.26g) in isopropanol (20 ml) is added. The temperature is increased to 80°C and stirring is continued for 2 hours. The coated pigment is isolated by filtration, washed with water and kept as presscake. The presscake is dried at 65°C in an oven just prior to testing. The product obtained is found to have improved powder storage stability compared with the untreated pigment (see Table 3).

Example 6

C.I. Pigment Yellow 74 aqueous presscake (32% solids, 188g) is redispersed in water (700 ml) in a conventional manner. To the resulting aqueous suspension at room temperature is added a solution of a poly(N-vinyl-2-pyrrolidone) having a number average molecular weight of 38,000 (6.0g, 10% on pigment weight) in water (350 ml). The mixture is stirred for 6 hours at room temperature, after which the temperature of the mixture is raised to 80°C and stirring continued for a further 90 minutes. The coated pigment is isolated by filtration, washed with water and kept as presscake. The presscake is dried at 65°C just prior to testing. The product obtained is found to have improved powder storage stability compared with the untreated pigment (see Table 3).

Example 7

CI Pigment Yellow 74 aqueous presscake (26% solids) (270g) is redispersed in water (500ml) in a conventional manner. To the aqueous suspension obtained is added a solution of 10.5g of Zinpol 1519 - 40% - W/IPA - a 40% solution of a polyacrylic acid in water/isopropanol available from Worlée Chemie - in water (60g) and the mixture is stirred and boiled at 99°C for 15 minutes. A solution of zinc acetate (1.4g) in water (60g) is added and the pH of the mixture is adjusted to 9.0 with dilute aqueous sodium hydroxide. The mixture is boiled at 99°C for a further 15 mins and then cooled to 70°C. The coated pigment is isolated by filtration, washed with water and dried at 70°C. The dried product is sieved, tested and found to have improved powder storage stability (see Table 4).

Example 8

CI Pigment Yellow 74 aqueous presscake (26% solids) (270g) is redispersed in water (500ml) in a conventional manner. To the aqueous suspension obtained is added a solution of a polyvinyl alcohol having a num-

ber average molecular weight of 18,000 (4.2g) in water (50g) and the mixture is stirred and boiled at 99°C for 15 mins. A solution of sodium orthophosphate (1.4g) in water (50g) is added and the pH of the mixture is adjusted to 8.0 with dilute aqueous sodium hydroxide. The mixture is boiled at 99°C for a further 15 mins and then cooled at 70°C. The coated pigment is isolated by filtration, washed with water and dried at 70°C. The dried product is sieved, tested and found to have improved powder storage stability (see Table 4).

Example 9

CI Pigment Yellow 74 aqueous presscake (26% solids) (270g) is redispersed in water (500ml) in a conventional manner. To the aqueous suspension obtained is added a solution of Zinpol 1519 - 40% - W/PA (10.5g) in water (50g) and the mixture is stirred and boiled at 99°C for 15 mins and then cooled to 70°C. The coated pigment is isolated by filtration, washed with water and dried at 70°C. The dried product is sieved, tested and found to have improved powder storage stability (see Table 4).

Example 10

To CI Pigment Yellow 74 aqueous slurry (5% pigment) (350g) is added a solution of a polyvinyl alcohol having a number average molecular weight of 18,000 (17.5g) in water (100ml). The slurry is heated at 99°C for 2 hours. A solution of zirconium acetate (32g of a 22% ZrO_2 solution) in water is added and heating continued for 5 mins. The coated pigment is isolated by filtration, washed with water and dried at 68°C in an oven. The dried product is sieved and tested and found to have improved powder storage stability compared with the untreated pigment (see Table 5).

Examples 11 to 19

To determine the powder storage stability of pigments treated by the method of the invention, as well as the corresponding untreated pigment, the dried pigments are incorporated in a conventional manner into an alkyd paint system (SORBAL P470, an alkyd resin ex DSM Resins Ltd having a solids content 70%, white spirit, pigment, and driers solution).

	<u>MILLBASE</u>	<u>FINAL PAINT</u>
PIGMENTATION	20%	10%
PIGMENT/BINDER	1/1.4	1/4.7
SOLIDS CONTENT	35%	54%

The dried powders are each divided into two portions. One portion is tested in the above paint system immediately after drying. The other portion is stored at 40°C for 1 month before the paint is prepared.

The tinting strengths are assessed visually and instrumentally using datacolour DC-3890.

The results are given in Tables 1 to 5. The values correspond to the parts of pigment required to give an equal tinting strength to a defined standard. Lower values denote higher tinting strengths.

Table 1

<u>Example</u>	<u>Pigment</u>	<u>Amount of Pigment Required</u>		<u>Loss of Strength</u>
		<u>Initial</u>	<u>1 month</u>	
Control	CI Pigment Yellow 74	80	103	23
11	Example 1	95	107	12
12	Example 3	100	102	2

Table 2

<u>Example</u>	<u>Pigment</u>	<u>Amount of Pigment Required</u>		<u>Loss of Strength</u>
		<u>Initial</u>	<u>1 month</u>	
Control	CI Pigment Yellow 74	77	82	5
13	Example 4	82	82	0

Table 3

<u>Example</u>	<u>Pigment</u>	<u>Amount of Pigment Required</u>		<u>Loss of Strength</u>
		<u>Initial</u>	<u>1 month</u>	
Control	CI Pigment Yellow 74	62	80	18
14	Example 5	78	89	11
15	Example 6	60	73	13

Table 4

<u>Example</u>	<u>Pigment</u>	<u>Amount of Pigment Required</u>		<u>Loss of Strength</u>
		<u>Initial</u>	<u>1 month</u>	
Control	CI Pigment Yellow 74	80	95	15
16	Example 7	125	130	5
17	Example 8	80	85	5
18	Example 9	120	120	0

Table 5

<u>Example</u>	<u>Pigment</u>	<u>Amount of Pigment Required</u>		<u>Loss of Strength</u>
		<u>Initial</u>	<u>1 month</u>	
Control	CI Pigment Yellow 74	107	125	18
19	Example 10	93	95	2

Claims

1. A method of improving the storage stability of a coloured organic pigment in powder form which comprises coating pigment particles with a solid polymer which is a polar group - containing vinyl polymer, said polar group being a hydroxy, carboxyl, carboxylic ester, anhydride or carboxamide group, or a cellulosic polymer, thereby inhibiting reduction of tinting strength of the pigment on storage.
2. A method according to claim 1, in which the polymer is a polyhydroxy vinyl polymer, a polycarboxy vinyl polymer, a N-vinyl pyrrolidone polymer or a cellulose ether.
3. A method according to claim 2, in which the polymer is a polyvinyl alcohol, a polyacrylic acid, a homopolymer of N-vinyl-2-pyrrolidone, or ethylcellulose.
4. A method according to any of claims 1 to 3, in which the solid polymer, or a solution or dispersion thereof

in a liquid, is mixed with a dispersion of the pigment until pigment particles are coated with the polymer, and coated pigment particles are separated from the resulting mixture.

- 5 5. A method according to claim 4, in which a solution of the polymer in water, a water-miscible organic solvent or a mixture of water and said solvent is mixed with an aqueous dispersion of the pigment.
6. A method according to any of claims 1 to 5, in which the polymer coating on the pigment particles is cross-linked by treatment of the polymer with a crosslinking agent therefor.
- 10 7. A method according to claim 6, in which the crosslinking agent is a boric acid or a salt thereof, a phosphoric acid or a salt thereof, a silicon (IV) trialkoxide or tetra-alkoxide, a silicate which forms active silica on hydrolysis, an aluminate which forms alumina on hydrolysis, a zirconium (IV) compound or a zinc compound.
8. A method according to claim 7, in which the crosslinking agent is boric acid, sodium tetraborate, sodium orthophosphate, 3-(trimethoxysilyl)propyl methacrylate, sodium silicate, zirconium (IV) acetate or zinc acetate.
- 15 9. A method according to any of claims 6 to 8, in which the crosslinking agent or a solution thereof in water, a water-miscible organic solvent or a mixture thereof is mixed with an aqueous dispersion of the polymer-coated pigment and, after crosslinking, pigment particles having a crosslinked coating are separated from the resulting reaction mixture.
- 20 10. A method according to claim 9, in which the mixture of the aqueous dispersion of the polymer-coated pigment and the crosslinking agent has a pH from 7 to 10.
- 25 11. A particulate composition comprising particles of a coloured organic pigment coated with a crosslinked solid polar group-containing vinyl polymer, said polar group being a hydroxy, carboxyl, carboxylic ester, anhydride or carboxamide group.
- 30 12. A composition according to claim 11, in which the polymer is a polyvinyl alcohol crosslinked by a boric acid or a salt thereof, a phosphoric acid or a salt thereof, a silicon (IV) trialkoxide or tetra-alkoxide, a silicate which forms active silica on hydrolysis, an aluminate which forms alumina on hydrolysis, or a zirconium (IV) compound, or the polymer is a polyacrylic acid crosslinked by a zinc compound.
- 35 13. Use of a solid polymer, which is a polymer as specified in any of claims 1 to 3, as a powder stabilising coating on coloured organic pigment particles, thereby inhibiting reduction of tinting strength of the pigment on storage.
- 40 14. Use according to claim 13, in which the polymer is crosslinked.
15. A high molecular weight material pigmented with a composition according to claim 11 or 12.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 30 7235

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 296 107 (CIBA-GEIGY AG) * the whole document *	1-10, 13, 14	C09B67/08
D	& US-A-4 889 562 ---		
X	EP-A-0 296 106 (CIBA-GEIGY) * the whole document *	1-10, 13, 14	
P, X	EP-A-0 466 646 (CIBA-GEIGY AG) * page 3, line 14 - line 51; examples 7, 18 * claims 1, 2, 16 *	1-15	
A	EP-A-0 242 754 (BASF AG) * column 1, line 1 - column 3, line 40; examples *	1-5	
A	EP-A-0 022 746 (SANDOZ) * the whole document *	1-5	
A	EP-A-0 323 407 (CIBA-GEIGY) * example 5 *	1	
A	DE-B-1 270 208 (GENERAL ANILINE AND FILM CORP.) * column 2, line 45 - column 3, line 11; examples *	1	
A	US-A-3 904 562 (HOPFENBERG ET. AL.) * the whole document *	1	C09B C09D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 08 DECEMBER 1992	Examiner KETTERER M.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (11.82) (P0401)